

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
<b>Gun Metal</b>													
C83300	92-94	1-2	1-2	2-6									
C83450	87-89	2.2-3	1.5-2.5	5.5-7.5	0.25	0.8-1.5	0.03	0.005		0.005	0.25	0.08	
C83500	86-88	5.5-6.5	3.5-5.5	1-2.5	0.25	0.5-1	0.03	0.005		0.005	0.25	0.08	
C83600	84-86	4.3-6	4-5.7	4.3-6	0.25	1	0.05	0.005		0.005	0.25	0.08	
C83800	82-83.5	3.5-4.2	5.8-6.8	5.5-8	0.25	1	0.03	0.005		0.005	0.25	0.08	
C83810	Rem.	2-3.5	4-6	7.5-9.5	0.5	2		0.005		0.1			
C84200	78-82	4-6	2-3	10-16	0.4	0.8	0.05	0.005		0.005	0.25	0.08	
C84400	79-82	2.5-3.5	6-8	7-10	0.4	0.8	0.02	0.005		0.005	0.25	0.08	
C84410	Rem.	3-4.5	7-9	7-11		1		0.01		0.2			0.05
C84500	77-79	2-4	6-7.5	10-14	0.4	1	0.02	0.005		0.005	0.25	0.08	
C84800	75-76.7	2-3	5.5-7	13-17	0.4	1	0.02	0.005		0.005	0.25	0.08	
C92210	86-89	4.5-5.5	1.7-2.5	3-4.5	0.25	0.7-1	0.03	0.005		0.005	0.2	0.05	
C92220	86-88	5-6	1.5-2.5	3-5.5	0.25	0.5-1	0.05						
C54400	Rem.	3.5-4.5	3.5-4.5	1.5-4.5	0.1		0.01-0.5						