

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	Impurities
IS:1458-1965												
Leaded Bz. Class-3	Rem.	6-8	14-16	0.5	0.3		0.05	0.01			0.4	0.7
Leaded Bz. Class-4	Rem.	6-8	9-11	0.5	0.3		0.05	0.01			0.4	0.7
Leaded GM. Class-5	Rem.	4-6	4-6	4-6	0.3		0.05	0.01			0.3	0.6
IS:318-1981												
LTB-3	Rem.	6-8	9-11	0.75	0.35	2		0.01		0.02	0.5	0.8
LTB-4	Rem.	6-8	14-16	0.75	0.35	2				0.02	0.5	0.8
LTB-5	Rem.	9-11	8.5-11	1	0.35	2		0.01		0.02	0.5	0.8
LTB-6	Rem.	4-6	18-23	1	0.35	2				0.01	0.5	0.8