

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	Impurities
Tin Bronze	IS:28-1985											
Ph. Bz (Grade - 1)	Rem.	6-8	0.25	0.5	0.3	0.7	0.3-0.5	0.01		0.02	0.1	1.2
Ph. Bz (Grade - 2)	Rem.	10 Min	0.25	0.05	0.1	0.1	0.5 Min	0.01		0.02		0.6
Ph. Bz (Grade - 3)	Rem.	6.5-8.5	2-5	2		1	0.3 Min					0.5
Ph. Bz (Grade - 4)	Rem.	9-11	0.25	0.05		0.25	0.15					0.8
Ph. Bz (Grade - 5)	Rem.	11-13.1	0.5	0.3	0.15	0.5	0.15 min	0.01		0.02		2